



FEM Simulation of Influence of Protective Encapsulation on MEMS Pressure Sensor

Yao, Qingshan; Janting, Jakob; Branebjerg, Jens

Published in:
Proceedings of Workshop on MEMS Sensor Packaging

Publication date:
2003

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Yao, Q., Janting, J., & Branebjerg, J. (2003). FEM Simulation of Influence of Protective Encapsulation on MEMS Pressure Sensor. In *Proceedings of Workshop on MEMS Sensor Packaging*

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

FEM Simulation of Influence of Protective Encapsulation on MEMS Pressure Sensor

Qingshan Yao^a, Jens Branebjerg^b, Jakob Janting^c

^a*SensoAsian Industrial Consulting, Hostrupsvej 6a, DK-3400, Hilleroed, Denmark
e-mail: sensoasian@hotmail.com, Fax: +45 45 93 72 88*

^b*DELTA Danish Electronics, Light & Acoustics, Venlighedsvej 4, DK-2970 Hoersholm, Denmark
e-mail: jab@delta.dk, Fax: +45 72 19 40 01, URL: <http://www.delta.dk>*

^c*DELTA Danish Electronics, Light & Acoustics, Venlighedsvej 4, DK-2970 Hoersholm, Denmark
e-mail: jaj@delta.dk, Fax: +45 72 19 40 01, URL: <http://www.delta.dk>*


ABSTRACT

The objective of the work is to evaluate the feasibility of packaging a MEMS silicon pressure sensor by using either a polymer encapsulation or a combination of a polymer encapsulation and a metallic protection Membrane (fig. 1). The potential application of the protected sensor is for harsh environments. Several steps of simulation are carried out:

1) Comparisons of the sensitivities are made among the non-encapsulated silicon sensor, the polymer encapsulated and polymer with metal encapsulated sensor. This is for evaluating whether the encapsulating materials reduce the pressure sensitivity compared to the conventionally exposed sensor.

2) Stress concentration calculations are performed to investigate if the encapsulation could lead to increased stress concentration in the silicon structure. The reliability of the adhesion of the metallic encapsulating membrane is assessed by investigating whether the metallic membrane / coating will peel off when applying the maximum pressure, which is 4000 bar leading to high shear stress between the metallic membrane and the polymer encapsulation material.

3) Thermal calculations are made to evaluate the influence of the environment on the packaged sensor.



Sensitivity related conclusion remarks:

- The polymer and the metallic encapsulation would not lead to a significant reduction of the sensitivity of the silicon sensor.
- Metallic encapsulation has a negligible influence on the sensitivity compared to the polymer-encapsulated design without the metal protection membrane.

Stress concentration related conclusion remarks:

- The coating leads to larger stresses on the interface between the two silicon parts of the sensor die.
- The coating leads to larger stresses in the junction region between the silicon sensor die and the mounting material.
- Whether the stress concentration on the interface between the metallic membrane and the polymer lead to a reliability risk depends on the adhesion of the membrane.
- The polymer encapsulation leads to much larger vertical displacement of the silicon sensor, which might harm the reliability of the mounting of the sensor die to the substrate.

Thermal related conclusion remarks:

- For the currently selected polymer encapsulation material with a thermal expansion coefficient of $5 \cdot 10^{-5}$, the temperature-induced deformation has significant influence on the sensitivity. A temperature change of 15 °C will give a signal as a pressure of 40 bars.

Acknowledgement

This work has been part of the collaboration on development of microsystems (SUM) project between two Danish institutes DELTA, the Microelectronics Centre (MIC), and four Danish companies Capres A/S, SonionMEMS A/S, Danfoss A/S and Grundfos A/S. The project is financially supported by the Danish Agency for Trade and Industry.